

Test Report No. BTX 102301(1)/PS/06

Date: 31 July 2006


Page 1 of 2

VAVERIET UDDEBO AB
92 UDDEBO
SE-514
SWEDEN

The following sample was submitted and identified by the client as:

<u>Sample Description:</u>	Sample of Flex fabric
<u>Details of Sample:</u>	Invoice 80909, Ref: Ulrika, Order No: 89343, Del Note No: 12840
<u>Date Sample(s) Received:</u>	14 July 2006
<u>Testing Period:</u>	Tested between 14/07/06 and 19/07/06
<u>Test(s) Requested:</u>	BS 5852:1990-Igniton source 5
<u>Test Results:</u>	Detailed in Appendix A
<u>Comments/Conclusions:</u>	The composite tested complies with the requirements of BS 5852:1990-ignition source 5.

Signed for and on behalf of
SGS United Kingdom Ltd



Paula Smith
Textile Technologist
Softlines Department

"This document is issued by the Company subject to its General Conditions of Service available on request and accessible at www.sgs.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein. Unless otherwise stated: (a) the results shown in this document refer only to the sample(s) tested and (b) such sample(s) are retained for 30 days only. This document cannot be reproduced except in full, without prior approval of the Company."

Tests denoted with an * have been subcontracted to another UKAS Approved Laboratory. Tests marked [Non UKAS Accredited] in this Report/Certificate are not included in the UKAS Accredited Schedule for our Laboratory

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation

Appendix A: Test Results

Flammability in accordance with BS5852: 1990

The sample was tested in the "as received" state using a combustion modified foam in-fill of approximate density 35 kg/cu. m.

The following test results relate only to the ignitability of the combination of upholstery composites (section 4 of BS5852: 1990) under the particular conditions of test stated; they are not intended as a means of assessing the full potential fire hazard of the materials or products in use.

Ignition Source No.5 (Wood crib) (BS5852 : 1990)

	Test 1	Test 2	Result
Duration of afterflame (min: secs)	5:15	4:58	PASS
Duration of smoking/glowing (min: secs)	6:06	5:15	
All flaming, and smoking ceased within 10 minutes of the ignition of the crib and no progressive smouldering was observed 60 minutes after the ignition of the crib.	Yes	Yes	

*** End of Report***