



**FIRE
TECHNOLOGY
SERVICES**

Confidential Report

Our Ref: 27/03694A/10/15

Notified Body
for PPE Directive,
Construction Products
Regulation & Marine
Equipment Directive
I.D. No. 0338 & 0339

**Fire Technology Services
A division of BTTG T & C Ltd
Wira House, West Park Ring Road,
Leeds, LS16 6QL**

Tel No: +44 (0)113 2591999



1066



FIRE TECHNOLOGY SERVICES

BTTG Testing & Certification Ltd.
Wira House
West Park Ring Road
Leeds, LS16 6QL
England

Tel: +44 (0)113 259 1999
Web: <http://www.bttg.co.uk>
Email: CSLeeds@bttg.co.uk

27 October 2015

Our Ref: 27/03694A/10/15
Your Ref:

Page 1 of 6

Client: Svensson
AB Ludvig Svensson
Bangatan 8
SE – 511 82 Kinna
Sweden

Job Title: **Fire Test on One Sample of Fabric**

Clients Order Ref: ---

Date of Receipt: 19 October 2015

Description of Sample: One sample of fabric, referenced: **Era**.

Work Requested: Fire Technology Services were requested to carry out a fire test on the sample supplied to BS 5852 Crib 5.





FIRE TECHNOLOGY SERVICES

BTTG Testing & Certification Ltd.
Wira House
West Park Ring Road
Leeds, LS16 6QL
England

Tel: +44 (0)113 259 1999
Web: <http://www.bttg.co.uk>
Email: CSLeeds@bttg.co.uk

27 October 2015

Page 2 of 6

Our Ref:
Your Ref:

Svensson

FIRE TESTS ACCORDING TO BS 5852:2006 (2011)

Methods of test for assessment of the ignitability of upholstered seating by smouldering and flaming ignition sources

Date of Test: 27/10/2015

Pre-Treatment

The material was subjected to the water soak procedure according to BS 5852:Annex E:2006 (2011).

Conditioning

Immediately prior to testing the sample was placed in indoor ambient conditions for 72 hours and then conditioned in a standard atmosphere of $20 \pm 5^\circ\text{C}$ temperature and $50 \pm 20\%$ relative humidity for at least 16 hours.

The sample was tested in a room of volume 25m^3 and 23°C

Procedure

The test was carried out in accordance with BS 5852:2006. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The specimen of fabric was mounted over fillings of combustion modified high resilience foam of density about 35 kg/m^3 .

The test was made using ignition source 5 in accordance with Section 11 'Methods of test for the ignitability of upholstery composites' and pass classifications were assigned for each ignition source if the performance requirements stated below were met.





27 October 2015

Page 3 of 6

Our Ref:
Your Ref:

Svensson

Requirements

Ignition Source	Maximum duration allowed for progressive smouldering	Maximum duration allowed for flaming
2 3	15 min after removal of burner tube	120 seconds after removal of burner tube
4 5	60 minutes after ignition of wood crib	10 minutes after ignition of wood crib
6 7	60 minutes after ignition of wood crib	13 minutes after ignition of wood crib

Failure also occurs if:

- smouldering or flaming necessitates forcible extinction due to escalating combustion behaviour so it is unsafe to continue
- flaming or smouldering essentially consumes the specimen within the test duration
- smouldering reaches the extremities of the specimen, that is to either side or to the full thickness of the filling
- flaming reaches the extremities of the specimen other than the top of the vertical part of the test specimen
- flaming passes through the full thickness of the specimen within the test duration
- any specimen that on final examination shows evidence of charring, within the filling 100 mm from the nearest part of the original position of the source
- any debris that causes an isolated floor fire that does not meet the requirements stated in the above table



FIRE TECHNOLOGY SERVICES

BTTG Testing & Certification Ltd.
Wira House
West Park Ring Road
Leeds, LS16 6QL
England

Tel: +44 (0)113 259 1999
Web: <http://www.bttg.co.uk>
Email: CSLeeds@bttg.co.uk

27 October 2015

Page 4 of 6

Our Ref:
Your Ref:

Svensson

Results

The test results relate only to the ignitability of the combination of upholstery composites under the particular conditions of test. They are not intended as a means of assessing the full potential fire hazard of the materials or products in use.

	Source 5	
	(Top)	
Time of ignition(s)	22	60
Time of Flame Extinction(s)	280	250
Time of Smoke Extinction(s)	480	460
Time of cover split(s)	DNO	90
Damage on seat width (mm)	140	170
Damage on seat length (mm)	130	105
Damage on seat depth (mm)	55	50
Damage on back width (mm)	170	150
Damage on back length (mm)	405	405
Damage on back depth (mm)	50	60
Melting (Yes or No)	Yes	Yes
Dripping (Yes or No)	No	No
Charring (Yes or No)	Yes	Yes
Other Phenomena		
Pass/Fail	Pass	Pass

DNO Did not observe time of event





FIRE TECHNOLOGY SERVICES

BTTG Testing & Certification Ltd.
Wira House
West Park Ring Road
Leeds, LS16 6QL
England

Tel: +44 (0)113 259 1999
Web: <http://www.bttg.co.uk>
Email: CSLeeds@bttg.co.uk

27 October 2015

Page 5 of 6

Our Ref:
Your Ref:

Svensson

Comment

The results indicate that the above sample met the performance requirements for source 5

Uncertainty of measurement has not been taken into account when presenting the test result. The relevant uncertainty value is included as an annex which forms an integral part of the report.

Reported by:.....*23. March*..... B Marsden (Mrs), Fire Technician

Countersigned by:.....*[Signature]*..... P Doherty, Operational Head

Enquiries concerning this report should be addressed to Customer Services.





FIRE
TECHNOLOGY
SERVICES

BTTG Testing & Certification Ltd.
Wira House
West Park Ring Road
Leeds, LS16 6QL
England

Tel: +44 (0)113 259 1999
Web: <http://www.bttg.co.uk>
Email: CSLeeds@bttg.co.uk

27 October 2015

Page 6 of 6

Our Ref:
Your Ref:

Svensson

Uncertainty Budget - Annex

The overall uncertainty budget for BS 5852:2006 (2011) is as follows:-

Measurements: $\pm 2\text{mm}$
Timings: ± 2 seconds.

