



**Client:** AB Ludvig Svensson  
Bangatan 8  
SE-511 82 Kinna  
Sweden

**Entry No:** 44684  
**Date received:** 23/09/2010

**Client's Description:** Sample of fabric article 1563964, Ink, composition 85% wool, 15% PA

**TEST REPORT**

**Test Required:** Flammability in accordance with IMO A.652 (16)  
**Pre-treatment:** None  
**Conditioning:** A minimum of 96 hours at 50 +/- 20% Relative Humidity, 20 +/- 5°C  
**Date of Test:** 28/09/2010

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Ignition Source	Observations	Result
<b>Smouldering cigarette</b>	No flaming or progressive smouldering was observed within one hour of placement of the cigarettes.	PASS
<b>Butane flame</b>	Flaming ceased within the specified two minute period after removal of the butane flame and no progressive smouldering occurred.	PASS

**Note:** A 20-22kg/m<sup>3</sup> non-fire retardant polyurethane foam was used as the filling.

-----End of Document-----

*This is hereby certified to be a correct return of the tests made of the items referred to herein.*



1104

G Briggs  
Head of Laboratory  
30<sup>th</sup> September 2010

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (\*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

