



FIRE  
TECHNOLOGY  
SERVICES

## Confidential Report

**Our Ref: 30/06234**

Notified Body  
for PPE Directive,  
Construction Products Directive  
& Marine Equipment Directive  
I.D. No. 0338 & 0339

**BTTG Fire Technology Services**  
Unit 4B Stag Industrial Estate, Atlantic Street,  
Broadheath, Altrincham, Cheshire, WA14 5DW

Tel: +44(0)161 929 8056 Fax: +44(0)161 929 8070



1066



FIRE  
TECHNOLOGY  
SERVICES

Unit 4B Stag Industrial Estate  
Atlantic Street, Broadheath  
Altrincham, Cheshire  
WA14 5DW, England

Tel: +44 (0)161 929 8056  
Fax: +44 (0)161 929 8070  
Web: [www.bttg.co.uk](http://www.bttg.co.uk)  
Email: [info@bttg.co.uk](mailto:info@bttg.co.uk)

31 May 2012

Page 1 of 2

**Our Ref:** 30/06234

**Client:** AB Ludvig Svensson  
Bangatan 8  
SE-511 82 Kinna  
Sweden

**Job Title:** Flammability testing of one woven fabric

**Clients Order Ref:** Letter 21 May 2012 and Emails 25 May 2012

**Date of Receipt:** 24 May 2012

**Description of Sample:** 100% Trevira CS woven fabric, referenced:  
Nova

**Work Requested:** Testing to BS 5867-2: 2008 Type "B" performance requirements  
(tested in the "as received" condition only)





Unit 4B Stag Industrial Estate  
 Atlantic Street, Broadheath  
 Altrincham, Cheshire  
 WA14 5DW, England

Tel: +44 (0)161 929 8056  
 Fax: +44 (0)161 929 8070  
 Web: www.bttg.co.uk  
 Email: info@bttg.co.uk

31 May 2012

Page 2 of 2

Our Ref: 30/06234  
 AB Ludvig Svensson

**Sample:** 100% Trevira CS woven fabric, referenced:  
 Nova

**Performance Standard:** BS 5867-2: 2008 Type "B" performance requirements

**Test Method:** BS EN ISO 15025: 2002  
 Flame application time = 15s

**Face Tested:** Test flame applied to "outer" face

**Cleansing Pretreatment:** None (tested in the "as received" condition only at the request of the client)

**Summary of Results:**

Date of test: 31 May 2012      Laboratory temperature: 20°C      Laboratory relative humidity: 58%

Specimen	1↑	2↓	3↑	4→	5←	6→
Flaming to edge	No	No	No	No	No	No
Afterflame time, sec	0	0	0	0	0	0
Afterglow spreads	No	No	No	No	No	No
Afterglow time, sec	0	0	0	0	0	0
Debris observed	No	No	No	No	No	No
Flaming debris	No	No	No	No	No	No
Hole formed	Yes	Yes	Yes	Yes	Yes	Yes
Holing to edge	No	No	No	No	No	No


**Assessment:**


BS 5867-2: 2008 Type "B" performance requirements

*No part of any hole nor any part of the lowest boundary of any flame shall reach the top edge or either vertical edge of the sample. If any part of any hole or any part of the lowest boundary of any flame, reaches the top edge or either vertical edge, or if there is any separation of flaming debris droplets in the testing of one specimen, a further six specimens shall be tested. If all six new specimens comply with the above requirements, the fabric shall be deemed to conform to the requirements for type "B" of this British standard.*

Tested in the "as received" condition this fabric complies with the requirements of BS 5867-2: 2008, Type "B" (subject to the proviso that the Clause 4 Sampling requirements have not been taken into account).

An estimation of uncertainty of measurement has not been taken into account when making a judgement to any pass/fail criteria.

Reported by:.....  ..... A Didycz, Laboratory Technician

Countersigned by:.....  ..... P M Eaton, Operational Head

