

# **Confidential Report**

Our Ref: 23/58930A/09/21





Telephone: +44 (0) 113 259 1999

Email: <u>info@bttg.co.uk</u> : <u>www.bttg.co.uk</u>

Date: 21 September 2021

Our Ref: 23/58930A/09/21

Your Ref:

Page: 1 of 4

Client: Ludvig Svensson AB

A: 511 82 Kinna Sweden

Job Title: Fire Test on One Fabric Sample

Clients Order Ref: --

Date of Receipt: 16 September 2021

Date Test Started: 21 September 2021


Description of Sample: One sample of fabric, which was referenced by the client as;

Article: Karat RE. Composition: stated to be 100% Recycled Trevira CS. Weight:

150g/m2.

Work Requested: We were asked to make the following fire test:

BS 5867: Part 2:Type B:2008 (2015)



<sup>\*\*</sup> subcontracted test, EN ISO/IEC 17025 accredited

Note: This report relates only to the samples submitted and as described in the report.



<sup>\*\*\*</sup> not UKAS accredited



Telephone: +44 (0) 113 259 1999

Email: <u>info@bttg.co.uk</u> : www.bttg.co.uk

Date: 21 September 2021

Our Ref: 23/58930A/09/21

Your Ref:

Page: 2 of 4

Client: Ludvig Svensson AB

BS 5867: Part 2: 2008 (2015): Type B Curtains, Drapes and Blinds

#### **Pre-treatment**

The sample was not subjected to any water soaking procedure.

## **Conditioning**

The test specimens were conditioned for at least 24 hours in the standard atmosphere of 65  $\pm$  5 % relative humidity (R.H.) and 20  $\pm$  2 °C.

## **Testing**

Three specimens from both length and width were tested in accordance with BS EN ISO 15025: Procedure A (surface ignition):2002.

Each specimen was subjected to an applied flame using propane and a 15 second flame application time. The results obtained (shown in the table below) were assessed according to the requirements of BS 5867: Part 2:Type B:2008 (2015).





Telephone: +44 (0) 113 259 1999

Email: <u>info@bttg.co.uk</u> : www.bttg.co.uk

Date: 21 September 2021

Our Ref: 23/58930A/09/21

Your Ref:

Page: 3 of 4

Client: Ludvig Svensson AB

## Results - Testing as received.

	Length			Width		
Specimen No.	1	2	3	4	5	6
Flame reached an edge	No	No	No	No	No	No
Hole reached an edge	No	No	No	No	No	No
Flaming debris separated	No	No	No	No	No	No
Afterflame (s)	0	0	0	0	0	0
Afterglow (s)	0	0	0	0	0	0

Requirements - Any "Yes" means fail except if only one specimen fails a further 6 specimens are tested, it the second 6 specimens all pass the result is a pass.

**Result: Pass** 





Telephone: +44 (0) 113 259 1999

Email: <u>info@bttg.co.uk</u> : <u>www.bttg.co.uk</u>

Date: 21 September 2021

Our Ref: 23/58930A/09/21

Your Ref:

Page: 4 of 4

Client: Ludvig Svensson AB

#### Comment

The fabric meets the Type B performance requirements of BS 5867: Part 2: 2008 – the fabric must be clearly labelled `If wetted in any way it is essential to re-treat the fabric to meet flammability requirements`.

The material should be identified with the manufacturers name, trademark or other identifying mark, the statement `Flammability complies with the requirements of BS 5867: Part 2, Type B and instructions of any special precautions to be taken concerning care (including cleansing) of the curtain, drape or window blind to be manufactured from the fabric, preferably using an appropriate care labelling symbol in accordance with BS EN 23758 and taking account of the pretreatment used in this test and the requirements of Clause 4 of BS 5867: Part 2: 2008 (2011). If the fabric is unsuitable for cleansing, this shall be stated.

An estimation of uncertainty of measurement has been taken into account when making a judgment to any pass/fail criteria. Under our Policy we have used a non-binary decision rule.

See our Decision rules Policy (<a href="http://www.bttg.co.uk/decision-rules-policy">http://www.bttg.co.uk/decision-rules-policy</a>) for further information.

### **Uncertainty Budget**

Measurements are not taken and pass/fail is related to flame extremities and flaming debris, as such any risk of false acceptance/false rejection is inherent with this standard and would be outside of 95% probability in any case. As such UoM is Zero providing all input parameters are correct.

There is no uncertainty budget associated with BS 5867:Part 2:Type B as no measurements are determined, the pass/fail criteria is assessed visually.

Reported by: B Bland, Technical Customer Services Officer

Countersigned by:...... P Doherty, Manager

Enquiries concerning this report should be addressed to Customer Services.



