

Test Report No. BTX 108705(1)/KD/07

Date: 19 May 2007

Page 1 of 2

VAVERIET UDDEBO AB  
92 UDDEBO  
SE-514  
SWEDEN

Attention: VAVERIET UDDEBO

The following sample was submitted and identified by the client as:

**Sample Description:** Sample of Mingel fabric

**Details of Sample:** No: 026579, Ref: Maria, Order No: 108652,

**Date Sample(s) Received:** 18 April 2007


**Testing Period:** Tested between 18/04/07 and 19/05/06

**Test(s) Requested:** BS 5852:1990-Igniton source 5

**Test Results:** Detailed in Appendix A

**Comments/Conclusions:** The composite tested complies with the requirements of BS 5852:1990-ignition source 5.

Signed for and on behalf of  
SGS United Kingdom Ltd



Paula Smith  
Textile Technologist  
Softlines Department

"This document is issued by the Company subject to its General Conditions of Service available on request and accessible at [www.sgs.com](http://www.sgs.com). Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein. Unless otherwise stated: (a) the results shown in this document refer only to the sample(s) tested and (b) such sample(s) are retained for 30 days only. This document cannot be reproduced except in full, without prior approval of the Company."

Tests denoted with an \* have been subcontracted to another UKAS Approved Laboratory. Tests marked [Non UKAS Accredited] in this Report/Certificate are not included in the UKAS Accredited Schedule for our Laboratory

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation

**Appendix A: Test Results**

**Flammability in accordance with BS5852: 1990**

The sample was tested in the "as received" state using a combustion modified foam in-fill of approximate density 35 kg/cu. m.

The following test results relate only to the ignitability of the combination of upholstery composites (section 4 of BS5852: 1990) under the particular conditions of test stated; they are not intended as a means of assessing the full potential fire hazard of the materials or products in use.

**Ignition Source No.5 (Wood crib) (BS5852 : 1990)**

	Test 1	Test 2	Result
Duration of afterflame (min: secs)	3:10	3:02	PASS
Duration of smoking/glowing (min: secs)	3:02	2:53	
All flaming, and smoking ceased within 10 minutes of the ignition of the crib and no progressive smouldering was observed 60 minutes after the ignition of the crib.	Yes	Yes	

**\*\*\* End of Report\*\*\***