



# TEXTILE LABORATORY SERVICES LIMITED

P.O. Box 50, Wharfebank Business Centre, Ilkley Road, OTLEY, LS21 3JP, United Kingdom

Tel: +44 (0)1943 850967 Fax: +44 (0)1943 850965 Email: info@tls-ltd.demon.co.uk

Regd. Office: 3 Victoria Road, Guiseley, England - No.1966147



The test report shall not be reproduced except in full, without written approval of the laboratory

## TEST CERTIFICATE

33742/8

### SAMPLE INFORMATION

Client **Ab Ludvig Svensson**  
Bangatan 8  
SE-511 82 Kinna  
SWEDEN.

Fabric Reference **Step, stated to be 75% wool, 25% viscose**  
Descriptions are information  
supplied by the client

Dimensions (approx) **250cm by 152cm full width**  
Sample received **2/12/2013**

**Testing to Clause 11 of BS 5852 : 2006 Assessment of the ignitability of upholstered seating by Smouldering and Flaming sources - Source 5 ( Crib 5)**

### PRE-TREATMENT

The material was subjected to a water soak according to Annex E of BS 5852 : 2006

### CONDITIONING

All materials used were conditioned and tested in the environments specified in Clause 10.1 of BS 5852 : 2006

### TESTING

Test results relate only to the sample tested. The material was tested according to **BS 5852 : 2006 Methods of test for the ignitability of upholstered composites for seating by flaming sources using Source 5 (Crib 5)**


Foam used:

**The sample was tested over combustion modified polyurethane foam with a density of approximately 36kg/m<sup>3</sup>, reference SB36/140**

It should be noted that the results of BS 5852 ; Part 2 : 1982 relate only to the ignitability of the combination of materials under test; they are not intended as a means of assessing the full potential fire hazard of the materials in use

The test results are shown in the tables below:





# TEXTILE LABORATORY SERVICES LIMITED


P.O. Box 50, Wharfebank Business Centre, Ilkley Road, OTLEY, LS21 3JP, United Kingdom

Tel: +44 (0)1943 850967 Fax: +44 (0)1943 850965 Email: info@tls-ltd.demon.co.uk

Regd. Office: 3 Victoria Road, Guiseley, England - No.1966147



Specimen no	1	2
<b>Duration of:</b>		
Ignition source	8'20"	8'25"
Flames	4'30"	4'34"
Smoke	8'20"	8'25"
<b>Time from start of:</b>		
Cover split	Did not split	Did not split
Extinction	8'20"	8'25"
Melting	No	No
Dripping	No	No
Charring	Yes	Yes
Progressive smouldering on final inspection	No	No
<b>Extent of damage (mm)</b>		
<b>Horizontal component</b>		
Width - left crib edge to left edge of burn	30	30
Width - right crib edge to right edge of burn	30	30
Width - front crib edge to front edge of burn	30	25
Depth	40	40
<b>Vertical component</b>		
Width - left crib edge to left edge of burn	30	35
Width - right crib edge to right edge of burn	30	35
Depth	35	40
<b>Max char distance</b>	<b>40</b>	<b>40</b>
<b>Smouldering criteria</b>		
Unsafe escalating combustion	No	No
Testing assembly consumed	No	No
Smoulders to extremities	No	No
Smoulders through thickness	No	No
Smoulders more than 1 hour	No	No
Char more than 100mm from source edge	No	No



# TEXTILE LABORATORY SERVICES LIMITED

P.O. Box 50, Wharfebank Business Centre, Ilkley Road, OTLEY, LS21 3JP, United Kingdom

Tel: +44 (0)1943 850967 Fax: +44 (0)1943 850965 Email: info@tls-ltd.demon.co.uk

Regd. Office: 3 Victoria Road, Guiseley, England - No.1966147



Specimen no	1	2
<b>Flaming criteria</b>		
Visible flames after 10 mins	No	No
Escalating flaming combustion	No	No
Testing assembly consumed	No	No
Flames to extremities	No	No
Flames through thickness	No	No
Progressive smouldering on final inspection	No	No
(All distance criteria exclude vertical)		
Any "Yes" in smouldering or flaming criteria = Ignition		
<b>Specimen result</b> (Ignition or Non-ignition)	<b>Non-Ignition</b>	<b>Non-Ignition</b>

## CONCLUSION

Since both specimens show Non-ignition the combination of materials is designated NI/5 (ie PASS)

Signed:.....

J. M. Brown C Chem MRSC C Text FTI  
Managing Director & Authorised Signatory

Checked by:.....