



Confidential Report

Our Ref: 23/62804B/01/25





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 12 February 2025

Our Ref: 23/62804B/01/25
Your Ref:

Page: 1 of 5

Client: AB Ludvig Svensson

Bangatan 8
511 82 Kinna
Sweden

Job Title: Fire Test on One Fabric Sample

Clients Order Ref:

Date of Receipt: 28 January 2025

Date Test Started: 12 February 2025

Description of Sample: One sample of fabric, which was referenced by the client as;
BonBon, 85% Wool, 15% Polyamide

Work Requested: We were asked to make the following fire test:

IMO FTP Code 2010:Part 8

* subcontracted test, UKAS accredited
** subcontracted test, EN ISO/IEC 17025 accredited
*** not UKAS accredited

Note: This report relates only to the items tested.



Date: 12 February 2025

Our Ref: 23/62804B/01/25
Your Ref:

Page: 2 of 5

Client: **AB Ludvig Svensson**

Product Description

Company Name	AB Ludvig Svensson
FABRIC	
Type of Furniture, e.g., Seat, Sofa, Office Chair, etc;.	-
Name and/or Identification of the Product Tested	BonBon
Materials of the Product and its Composite Ratio (i)	85% Wool 15% Polyamide
Composition of Weave (ii)	Plain
Density (Number/Inch) the Number of Threads per Inch in both warp and weft; and	Warp: 71 Weft: 64
Yarn Number Count	Nm 32/2
Thickness (mm)	-
Mass per Unit Area (g/m ²)	350
Colour and Tone (iii)	Orange / Grey
Method and Quantity of Fire Retardant Treatment (type and amount per m ²)	None
FILLINGS (if applicable)	
Material (Name of the Manufacturer, Type Designation);	N/A
Weight per Unit Volume (kg/m ³)	N/A
Method and Quantity of Fire Retardant Treatment (type and amount)	N/A

- (i) Such as wool, nylon, polyester, etc.
(ii) Such as plain, weave, twilled.
(iii) If the product has a pattern, the representative colour shall be described.



Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG® and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2025 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 12 February 2025

Our Ref: 23/62804B/01/25
Your Ref:

Page: 3 of 5

Client: AB Ludvig Svensson

Testing to IMO FTP Code 2010 : Part 8 Test for Upholstered Furniture

Conditioning

Immediately prior to testing the samples was placed in indoor ambient conditions for 72 hours and then conditioned in a standard atmosphere of $23\pm 2^{\circ}\text{C}$ temperature and $50\pm 5\%$ relative humidity for at least 16 hours.

The samples were tested in a room of volume 25m^3 and 19°C .

Procedure

The samples was tested in accordance with IMO FTP Code 2010:Part 8 using ignition sources 0 and 1. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The sample was tested over combustion modified polyurethane foam with a density of approximately $34\text{-}36\text{kg/m}^3$.

Requirements

Ignition Source 0 No progressive smouldering or flaming within 1 hour of the placement of the cigarette.

Ignition Source 1 All progressive smouldering and flaming to cease within 120 sec of removal of the burner tube.

Cigarette Specification (Source 0)

Dimensions (mm)	69mm x 8.0mm
Mass (g)	0.93
Smouldering Rate (mins/secs)	9m 54s



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG® and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2025 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 12 February 2025

Our Ref: 23/62804B/01/25
Your Ref:

Page: 4 of 5

Client: AB Ludvig Svensson

Results

Cigarette Test – Source 0

Specimen No.	1	2
Extinction Time (smouldering) (min)	DNP	DNP
Time of cover split	DNS	DNS
Melting (Yes/No)	No	No
Dripping (Yes/No)	No	No
Charring (Yes/No)	Yes	Yes
Progressive Smouldering (Yes/No)	No	No
Observations	DNP/DNS	DNP/DNS
Pass/Fail	PASS	PASS

Result of the Cigarette Test: Pass

Propane Flame Test – Source 1

Specimen No.	1	2
Time of Ignition (s)	4	4
Extinction time of flames after removal of burner (s)	1	3
Time to Cover Split (s)	DNO	DNO
Melting (Yes/No)	No	No
Dripping (Yes/No)	No	No
Charring (Yes/No)	Yes	Yes
Progressive smouldering (Yes/No)	No	No
Observations:	DNO	DNO
Pass/Fail	PASS	PASS

Result of the Flame Test: Pass

Acronym

DNP – Did not propagate
ES – Escalating smouldering
BTE – Burnt to extremities

EC – Escalating combustion
DNS – Material did not split

ME – Manually extinguished
DNO – Did not observe time of event



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG® and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2025 Shirley Technologies Limited. All rights reserved.



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: onestopshop@bttg.co.uk
Website: www.bttg.co.uk

Date: 12 February 2025

Our Ref: 23/62804B/01/25
Your Ref:

Page: 5 of 5

Client: AB Ludvig Svensson

Note

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Comment


In our opinion, based on the test carried out on the sample supplied; the results indicate that the sample meets the requirements according to IMO FTP Code 2010:Part 8.


Where required to make a judgement to any pass/fail criteria an estimation of uncertainty of measurement has been taken into account. Under our Policy we have used a non-binary decision rule.

See our decision rules Policy (<https://www.bttg.co.uk/about-us/decision-rules-policy/>) for further information.

Uncertainty Budget

Measurements: $\pm 2\text{mm}$
Timings: ± 2 seconds.

Reported by:  R Walls, Laboratory Technician

Countersigned by:  B Bland, Technical Customer Service Officer

Enquiries concerning this report should be addressed to Customer Services.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG® and Shirley® are trade names of Shirley Technologies Ltd.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2025 Shirley Technologies Limited. All rights reserved.