

Telephone: +44 (0)113 259 1999

Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 18 March 2021

Our Ref: 23/58295-1-2

Your Ref:

Page: 1 of 6

Client: AB Ludvig Svensson

Bangatan 8

SE - 511 82 Kinna

Sweden

Job Title: Fire test on one sample of fabric

Client's Order No:

Date of Receipt: 03 March 2021 Date of Test Start: 10 March 2021

Description of Sample(s): One sample of fabric identified as follows was received for testing:

Article: Ally, Weight: 320 g/m2, stated to be 85% Wool, 15% Polyamide

Work Requested: We were asked to make the following test:

IMO FTP Code 2010 Part 8 (Upholstered Furniture)





Telephone: +44 (0)113 259 1999

Email: <u>info@bttg.co.uk</u> Website: <u>www.bttg.co.uk</u>

Date: 18 March 2021

Our Ref: 23/58295-1-2 Your Ref: -

Page: 2 of 6

AB Ludvig Svensson

Sample was identified as follows:

Article: Ally, Weight: 320 g/m2, stated to be 85% Wool, 15% Polyamide

Testing to IMO FTP Code 2010: Part 8 – Test for Upholstered Furniture

Conditioning

Immediately prior to testing the samples was placed in indoor ambient conditions for 72 hours and then conditioned in a standard atmosphere of 23±2°C temperature and 50±5% relative humidity for at least 16 hours.

The samples were tested in a room of volume 25m³ and 17°C.

Procedure

The samples was tested in accordance with IMO FTP Code 2010: Part 8 using ignition sources 0 and 1. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The sample was tested over combustion modified polyurethane foam with a density of approximately 36 kg/m³.

Requirements

Ignition Source 0 No progressive smouldering or flaming within 1 hour of the placement of the cigarette

Ignition Source 1 All progressive smouldering and flaming to cease within 120 sec of removal of the burner

tube

Cigarette Specification (Source 0)

Dimensions (mm) 68mm x 8mm

Mass (g) 0.92 Smouldering Rate (mins/secs) 10.47





Telephone: +44 (0)113 259 1999

Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 18 March 2021

Our Ref: 23/58295-1-2 Your Ref: -

Page: 3 of 6

AB Ludvig Svensson

Product Description

| Type of Furniture, e.g., Seat, Sofa, Office Chair, etc;. | Upholstery |
|---|-------------------------|
| Name and/or Identification of the Product Tested | Ally |
| Materials of the Product and its Composite Ratio (i) | 85% Wool, 15% Polyamide |
| Composition of Weave (ii) | Plain |
| Density (Number/Inch) the Number of Threads per Inch in both warp and weft; and | Warp : 47 Weft : 28 |
| Yarn Number Count | Nm 18/2 |
| Thickness (mm) | |
| Mass per Unit Area (g/mm²) | 320 |
| Colour and Tone (iii) | Beige |
| Method and Quantity of Fire-Retardant Treatment | None |

- (i) Such as wool, nylon, polyester, etc.
- (ii) Such as plain, weave, twilled.
- (iii) If the product has a pattern, the representative colour shall be described.





Telephone: +44 (0)113 259 1999

Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 18 March 2021

Our Ref: 23/58295-1-2

Your Ref:

Page: 4 of 6

AB Ludvig Svensson

RESULTS

Sample Ref: Article: Ally, Weight: 320 g/m2, stated to be 85% Wool, 15% Polyamide

Cigarette Test - Source 0

| Specimen No. | 1 | 2 |
|-------------------------------------|------|------|
| Time of Ignition (s) | | |
| Extinction Time (smouldering) (min) | 24 | 24 |
| Time of cover split | DNS | DNS |
| Melting (Yes/No) | No | No |
| Dripping (Yes/No) | No | No |
| Charring (Yes/No) | Yes | Yes |
| Progressive Smouldering (Yes/No) | No | No |
| Pass/Fail | PASS | PASS |

Result of the Cigarette Test: PASS

Propane Flame Test - Source 1

| Specimen No. | 1 | 2 |
|---|------|------|
| Time of Ignition (s) | 6 | 7 |
| Extinction time of flames after removal of burner (s) | 1 | 1 |
| Time to Cover Split (s) | DNS | DNS |
| Melting (Yes/No) | No | No |
| Dripping (Yes/No) | No | No |
| Charring (Yes/No) | Yes | Yes |
| Progressive smouldering (Yes/No) | No | No |
| Pass/Fail | PASS | PASS |

Result of the Flame Test: PASS

Acronym

DNP – Did not propagate
ME – Manually extinguished
DNS – Material did not split
BTE – Burnt to extremities

EC – Escalating combustion ES – Escalating smouldering

DNO – Did not observe time of event





Telephone: +44 (0)113 259 1999

Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 18 March 2021

Our Ref: 23/58295-1-2

Your Ref: -

Page: 5 of 6

AB Ludvig Svensson

Comment

In our opinion, based on the test carried out on the sample supplied; the results indicate that the sample meets the requirements according to IMO FTP Code 2010, Part 8.

Uncertainty of measurement has not been taken into account when presenting the test result. The relevant uncertainty value is included as an annex which forms an integral part of the report.

Reported by: B Bland

Laboratory Technician

Countersigned By:.....

P Doherty Manager

Enquiries concerning this report should be addressed to Customer Services





Telephone: +44 (0)113 259 1999

Email: info@bttg.co.uk Website: www.bttg.co.uk

Date: 18 March 2021

Our Ref: 23/58295-1-2

Your Ref: -

Page: 6 of 6

AB Ludvig Svensson

Uncertainty Budget – Annex

The overall uncertainty budget IMO FTP Code 2010 : Part 8 is as follows:

Measurements: ±1mm Timings: ±2 seconds

