



Caroline Hultberg
Ludvig Svensson AB
Bangatan 8
51182 Kinna
Sverige

Sample received: 2018-02-07

Completed: 2018-02-07 - 2018-02-08

Test Report

Sample

Description: Blue woven fabric

Customers reference: Semi

Tests conducted

- Colour fastness to dry cleaning using perchloroethylene solvent (ISO 105 D01:2010)
-

Stockholm 2018-02-08

Ulrika Jansson
Test analyst

ulrika.jansson@textillab.se
08-6158386

Jan Svedberg
Technical manager

The test results relate only to the stated items.

This test report may not be reproduced other than in full, except with the prior written approval of the issuing laboratory.

(A) Accredited method

(A*) Analysis performed by subcontracted laboratory, accredited for the method.

(*) Analysis performed by subcontracted laboratory, not accredited for the method.



Test method and result

Method: Colour fastness to dry cleaning using perchloroethylene solvent (ISO 105 D01:2010)
Grade 1-5 of which 5 is best.

Result: Multifibre fabric: DW

Staining:

-acetate 4-5

-cotton 4-5

-polyamide 4-5

-polyester 4-5

-acrylic 4-5

-wool 4-5

Colour change: 4-5

(A) Accredited method

(A*) Analysis performed by subcontracted laboratory, accredited for the method.

(*) Analysis performed by subcontracted laboratory, not accredited for the method.