

CINQ

Design.....	Pepe Comi	
Material	100% Polyester, Trevira CS	
Care instructions	Remove dust with a damp cloth or a brush	
Max Width.....	300 cm (± 1%)	118" (± 1%)
Weight.....	135 g/m ² (± 5%)	3,98 oz/yd ² (± 5%)
Thickness.....	0,34 mm	13,4 mil
Standard Roll Length (approx)	50 m	55 yd
Breaking strength ISO 13934-1	Warp: 100-116 N	Weft: 290-315 N
Elongation to break ISO 13934-1	Warp: 22-27%	Weft: 15-17%
Fastness to light ISO 105B02 (Bluescale 1-8)	Class 5-7	
Openess factor	25%	

Flame retardant according to:

DIN 4102 (B1)

BS 5867: Part 2: 1980 (1993) Type B

EN 13773 Class 1

IMO FTP Code 2010: Part 7




0575




USAGE


Panels:



Rollerblinds:





Normal rolling



Reversed rolling

Maximum drop

Vertical stripes		Yes	Yes	Yes	Unlimited
		No	Yes ¹	Yes ¹	300 cm

All articles for indoor usage behind glass. Handle with care during sewing and installation, be sure to avoid wrinkles and crease.

1= Fabric rolls are rolled reverse side out.

Roller blind tube should be placed on the reverse side of the fabric to prevent curling.

CINQ	Solar optical properties (%) according to EN 14500					Thermal performance in combination with reference glazings from EN 14501							
						Glazing A		Glazing B		Glazing C		Glazing D	
	Colour	T _s	R _s	A _s	T _{vis}	T _{uv}	g _{tot}	U	g _{tot}	U	g _{tot}	U	g _{tot}
8000 White	56	40	4	55	39	0,55	3,94	0,53	2,33	0,47	1,11	0,27	1,08
6710 Off-White	48	45	7	48	32	0,51	3,82	0,50	2,28	0,45	1,10	0,26	1,07
6821 Beige	47	37	16	41	31	0,54	3,80	0,53	2,28	0,47	1,09	0,27	1,07
4030 Grey	46	35	19	37	30	0,55	3,79	0,54	2,27	0,48	1,09	0,27	1,07
8400 Dark-Gey	38	27	35	28	25	0,56	3,66	0,55	2,23	0,49	1,08	0,28	1,06
8900 Black	41	22	37	27	28	0,59	3,70	0,58	2,24	0,51	1,08	0,29	1,06

T_s = Solar Transmission

R_s = Solar Reflection

A_s = Solar Absorption

T_{vis} = Visible light Transmission

T_{uv} = Ultraviolet light Transmission

g_{tot} = Total solar energy transm. (0-1) 1=100%

U = Thermal transmittance W/m² K

Glazing A = Clear single glazing, g=0,863. U=5,88

Glazing B = Clear double glazing, g=0,762. U=2,88

Glazing C = Double glazing with low e coating, g=0,59. U=1,23

Glazing D = Refl. double glazing with low e coating, g=0,334. U=1,2