



Client: AB Ludvig Svensson
Bangatan 8
SE-511 82 Kinna
Sweden

Entry No: 45525
Date received: 04/01/2011

Client's Description: Sample of fabric 1463972, Name: Rami, Composition: 80% Wool, 20% Ramie

TEST REPORT

Test Required: Flammability in accordance with BS 5852 ignition source 5
Pre-treatment: None
Conditioning: A minimum of 96 hours at 50 +/- 5% Relative Humidity, 23 +/- 2°C
Method of Test: BS 5852 : 2006 Clause 11 (composites)
Date of Test: 11/01/2011

The following test results relate only to the ignitability of the combination of upholstery composites under the particular conditions of test. They are not intended as a means of assessing the full potential fire hazard of the materials in use.

Ignition Source	Observations	Result
5 (Wood Crib)	Flaming ceased within the specified ten minute period after ignition of the crib and no progressive smouldering occurred.	PASS

Note: A 35 kg/m³ CMHR Foam (Recticel RS35H) was used as the filling.

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein.



1104

G Briggs
Head of Laboratory
31st January 2011

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

