

OPAQ COLOUR

Design	Pepe Corni	
Material	100% Polyester,Trevira CS	
Care instructions	Remove dust with a damp cloth or a brush	
Width.....	300 cm (± 1%)	118" (± 1%)
Weight.....	124 g/m² (± 5%)	3,7 oz/yd² (± 5%)
Thickness	0,34 mm	13,4 mil
Standard Roll Length (approx)	50 m	55 yd
Breaking strength ISO 13934-1	Warp: 85-105 N	Weft: 450-600 N
Elongation to break ISO 13934-1	Warp: 35-55%	Weft: 10-15%
Fastness to light ISO 105B02 (Bluescale 1-8)	Class 5-7	
Openess factor	20%	

Flame retardant according to:

DIN 4102 (B1)
BS 5867: Part 2: Type B
EN 13773 Class 1
IMO FTP Code 2010: Part 7
NFP 92-503-507 (M1)*




0575





* Opaq Colour is based on Opaq, therefore flame retardancy properties are based on Opaq for this certificate.

USAGE

Panels:



Rollerblinds:



Normal rolling Reversed rolling **Maximum drop**

Vertical stripes
Horizontal stripes

	Yes	Yes	Yes	9 m²
	Not recommended	Yes¹	Yes¹	3 m

All articles intended for indoor usage behind glass. It is strongly recommended to use ultra sonic, laser or cutter with knife for cutting and shaping the screens. Handle with care during sewing and installation, be sure to avoid wrinkles and crease.

Fabric shade may vary slightly between batches.

1= Fabric rolls are rolled reverse side out. Roller blind tube should be placed on the reverse side of the fabric to prevent curling.

2= Svensson guarantee flawless cut measurements up to 9 m. Installations with cut measurements larger than 9 m are possible, but the customer is responsible for material cost due to increased fabric wastage.

OPAQ COLOUR	Solar optical properties (%) according to EN 14500					Thermal performance in combination with reference glazings from EN 14501							
						Glazing A		Glazing B		Glazing C		Glazing D	
Colour	Ts	Rs	As	T _{vis}	T _{uv}	g _{tot}	U	g _{tot}	U	g _{tot}	U	g _{tot}	U
4470	37	28	35	22	23	0,55	3,65	0,55	2,22	0,49	1,08	0,28	1,06
4330	41	42	17	30	26	0,50	3,70	0,50	2,24	0,46	1,08	0,26	1,06
5231	40	38	22	34	24	0,52	3,69	0,51	2,24	0,47	1,08	0,27	1,06
5570	35	24	41	24	23	0,57	3,62	0,56	2,21	0,50	1,08	0,28	1,05
6335	38	33	29	29	21	0,53	3,66	0,53	2,23	0,48	1,08	0,27	1,06
6635	40	32	28	30	23	0,54	3,69	0,54	2,24	0,48	1,08	0,27	1,06
3465	35	29	36	20	20	0,54	3,62	0,54	2,21	0,49	1,08	0,28	1,05
3670	39	25	36	23	23	0,57	3,67	0,56	2,23	0,50	1,08	0,28	1,06
3835	41	32	27	26	25	0,55	3,70	0,54	2,24	0,48	1,08	0,28	1,06
7080	36	26	38	21	21	0,56	3,63	0,55	2,22	0,49	1,08	0,28	1,05
6770	36	30	34	22	22	0,54	3,63	0,54	2,22	0,48	1,08	0,28	1,05
7030	44	35	21	36	27	0,54	3,75	0,53	2,26	0,48	1,09	0,27	1,07

Ts = Solar Transmission T_{uv} = Ultraviolet Transmission
Rs = Solar Reflection g_{tot} = Total solar energy transm. (0-1) 1=100%
As = Solar Absorption U = Thermal transmittance W/m² K
T_{vis} = Visible light Transm.

Glazing A = Clear single glazing, g=0,863, U=5,88
Glazing B = Clear double glazing, g=0,762, U=2,88
Glazing C = Double glazing with low e coating, g=0,59, U=1,23
Glazing D = Refl. double glazing with low e coating, g=0,334, U=1,2