

Confidential Report

Our Ref: 23/59235C/12/21





Wira House, West Park Ring Road, Leeds, LS16 6QL, UK. Telephone: +44 (0) 113 259 1999

Email: info@bttg.co.uk

: www.bttg.co.uk

Date: 12 January 2022

Our Ref: 23/59235C/12/21

Your Ref: ---

Page: 1 of 5

Client: Ludvig Svensson AB

A: 511 82 Kinna Sweden

Job Title: Fire Test on One Fabric Sample

Clients Order Ref: --

Date of Receipt: 23 December 2021

Date Test Started: 12 January 2022

Description of Sample: One sample of fabric, which was referenced by the client as;

Cody, stated to be 85% wool, 15% Polyamide. Weight: 280 g/m2

Work Requested: We were asked to make the following fire test:

IMO FTP Code 2010:Part 8

- * subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited

Note: This report relates only to the samples submitted and as described in the report.

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.

A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.

BTTGTM and Shirley® are trade names of Shirley Technologies Ltd.

The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.

Our laboratories are accredited to EN ISO/IFC 17025





Telephone: +44 (0) 113 259 1999

Email: info@bttg.co.uk : www.bttg.co.uk

Date: 12 January 2022

Our Ref: 23/59235C/12/21

Page: 2 of 5

Your Ref:

Client: Ludvig Svensson AB

Product Description

Company Name	Ludvig Svensson AB	
FABRIC		
Type of Furniture, e.g., Seat, Sofa, Office Chair, etc;.	Upholstery Fabric	
Name and/or Identification of the Product Tested	Cody	
Materials of the Product and its Composite Ratio (i)	85% wool, 15% Polyamide	
Composition of Weave (ii)	Plain	
Density (Number/Inch) the Number of Threads per Inch in both warp and weft; and	Warp: 71, Weft: 43	
Yarn Number Count	Nm 32/2	
Thickness (mm)		
Mass per Unit Area (g/m²)	280	
Colour and Tone (iii)	Beige	
Method and Quantity of Fire Retardant Treatment	None	
FILLINGS		
Material (Name of Manufacturer, Type Designation)		
Type of Filling Material (eg. Foam, Polyester Fibre etc.)		
Weight per Unit Volume (kg/m³)		
Method and Quantity of Fire Retardant Treatment		

- Such as wool, nylon, polyester, etc. (i)
- Such as plain, weave, twilled.
- (iii) If the product has a pattern, the representative colour shall be described.





Telephone: +44 (0) 113 259 1999

Email: <u>info@bttg.co.uk</u> : <u>www.bttg.co.uk</u>

Date: 12 January 2022

Our Ref: 23/59235C/12/21 Your Ref: ---

Page: 3 of 5

Client: Ludvig Svensson AB

Testing to IMO FTP Code 2010: Part 8

Test for Upholstered Furniture

Conditioning

Immediately prior to testing the samples was placed in indoor ambient conditions for 72 hours and then conditioned in a standard atmosphere of 23±2°C temperature and 50±5% relative humidity for at least 16 hours.

The samples were tested in a room of volume 25m³ and 16°C.

Procedure

The samples was tested in accordance with IMO FTP Code 2010:Part 8 using ignition sources 0 and 1. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The sample was tested over combustion modified polyurethane foam with a density of approximately 35-36kg/m³.

Requirements

Ignition Source 0 No progressive smouldering or flaming within 1 hour of the placement of the cigarette.

Ignition Source 1 All progressive smouldering and flaming to cease within 120 sec of removal of the burner tube.

Cigarette Specification (Source 0)

Dimensions (mm) 68mm x 8.0mm

Mass (g) 0.91 Smouldering Rate (mins/secs) 10m 47s





Telephone: +44 (0) 113 259 1999

Email: <u>info@bttg.co.uk</u> : <u>www.bttg.co.uk</u>

Date: 12 January 2022

Our Ref: 23/59235C/12/21 Your Ref: ---

Page: 4 of 5

Client: Ludvig Svensson AB

Results

Cigarette Test - Source 0

Specimen No.	1	2
Extinction Time (smouldering) (min)	DNP	DNP
Time of cover split	DNS	DNS
Melting (Yes/No)	No	No
Dripping (Yes/No)	No	No
Charring (Yes/No)	Yes	Yes
Progressive Smouldering (Yes/No)	No	No
Observations	DNS/DNP	DNS/DNP
Pass/Fail	PASS	PASS

Result of the Cigarette Test: Pass

Propane Flame Test – Source 1

Specimen No.	1	2
Time of Ignition (s)	6	7
Extinction time of flames after removal of burner (s)	2	1
Time to Cover Split (s)	DNO	DNO
Melting (Yes/No)	No	No
Dripping (Yes/No)	No	No
Charring (Yes/No)	Yes	Yes
Progressive smouldering (Yes/No)	No	No
Observations:	DNO	DNO
Pass/Fail	PASS	PASS

Result of the Flame Test: Pass

Acronym

DNP – Did not propagate ES – Escalating smouldering BTE – Burnt to extremities

IAC-MRA
UKAS
TESTING

EC – Escalating combustion DNS – Material did not split

ME – Manually extinguished DNO – Did not observe time of event

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.

A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.

BTTG™ and Shirley® are trade names of Shirley Technologies Ltd.

The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.

Our laboratories are accredited to EN ISO/IEC 17025.



Telephone: +44 (0) 113 259 1999

Email: <u>info@bttg.co.uk</u> : <u>www.bttg.co.uk</u>

Date: 12 January 2022

Our Ref: 23/59235C/12/21

Your Ref: ---

Page: 5 of 5

Client: Ludvig Svensson AB

Comment

In our opinion, based on the test carried out on the sample supplied; the results indicate that the sample meets the requirements according to IMO FTP Code 2010:Part 8.

An estimation of uncertainty of measurement has been taken into account when making a judgment to any pass/fail criteria. Under our Policy we have used a non-binary decision rule.

See our Decision rules Policy (http://www.bttg.co.uk/decision-rules-policy) for further information.

Uncertainty Budget

Measurements: ±2mm
Timings: ±2 seconds.

Reported by: B Bland, Technical Customer Services Officer

Countersigned by:..... P Doherty, Manager

Enquiries concerning this report should be addressed to Customer Services.

