

Telephone: +44 (0)113 259 1999

Email: <a href="mailto:info@bttg.co.uk">info@bttg.co.uk</a>
Website: <a href="mailto:www.bttg.co.uk">www.bttg.co.uk</a>

Date: 11 October 2019

Our Ref: 23/56872-1-1 Your Ref: -

Page: 1 of 4

Client: AB Ludvig Svensson

Bangatan 8 SE 511 82 Kinna Sweden

Job Title: BS EN 1021 Parts 1

Client's Order No:

Date of Receipt: 07 October 2019
Date of Test Start: 11 October 2019

Description of Sample(s): One sample of fabric identified as follows was received for testing:

Urban, stated to be 100% Trevira CS, 320g/m2

Work Requested: We were asked to make the following test:

BS EN 1021-1:2014 and BS EN 1021-2 2014





Telephone: +44 (0)113 259 1999

Email: <u>info@bttg.co.uk</u> Website: <u>www.bttg.co.uk</u>

Date: 11 October 2019

Our Ref: 23/56872-1-1
Your Ref: -

Page: 2 of 4

#### **AB Ludvig Svensson**

Sample was identified as follows:

Urban, stated to be 100% Trevira CS, 320g/m2

#### FIRE TESTS ACCORDING TO BS EN 1021-1:2014

Assessment of the ignitability of upholstered furniture. Part I. Ignition Source 0: Smouldering cigarette

#### **Pre-Treatment**

The samples received no pretreatment as the fabric is stated to be inherently flame retardant.

### Conditioning

After drying the sample was conditioned for at least 16 hours at a temperature of 23±2°C and relative humidity of 50±5%.

The sample was tested in a room of volume 25m<sup>3</sup> and 20°C.

### **Procedure**

The test was carried out in accordance with BS EN 1021-1:2014. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The sample was tested over non-fire retardant polyurethane foam with a density of approximately 20-22 kg/m<sup>3</sup>.

Tests were made using ignition source 0.

# Requirements

The specimens shall not:-

# **Smouldering Criteria**

- a) display escalating combustion requiring active extinction.
- b) smoulder or burn until it is essentially consumed within the test duration.
- c) smoulder or burn to the extremities of the specimen, or through the full thickness, within the duration of the test.
- d) smoulder for more than one hour.
- e) on final examination, show evidence of progressive smouldering.





Telephone: +44 (0)113 259 1999

Email: <u>info@bttg.co.uk</u> Website: <u>www.bttg.co.uk</u>

Date: 11 October 2019

Our Ref: 23/56872-1-1 Your Ref: -

Page: 3 of 4

# AB Ludvig Svensson

## Requirements (continued)

### Flaming Criteria

a) show evidence of flaming initiated by a smouldering source.

#### Results

	Cigarette			
	1	2	3 <sup>1</sup>	Comments
Smouldering Criteria (Yes/No)				
Unsafe escalating combustion	No	No	No	
Test assembly consumed	No	No	No	
Smoulders to extremities	No	No	No	
Smoulders through thickness	No	No	No	
Smoulders more than1 hour	No	No	No	
In final examination, presence of progressive smouldering	No	No	No	
Ignitability Performance (Yes/No)				
Occurrence of flames	No	No	No	
Ignition / Non Ignition ( I/NI )	NI	NI	NI	

<sup>&</sup>lt;sup>1</sup> Results for cigarette 3, only if applicable.

### Note

The test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

### Comments

A NI designation indicates that the sample meets the performance requirements of BS EN 1021-1.





Telephone: +44 (0)113 259 1999

Email: <a href="mailto:info@bttg.co.uk">info@bttg.co.uk</a>
Website: <a href="mailto:www.bttg.co.uk">www.bttg.co.uk</a>

Date: 11 October 2019

Our Ref: 23/56872-1-1 Your Ref: -

Page: 4 of 4

### **AB Ludvig Svensson**

## **Comments**

This report relates only to the samples submitted and as described in the report.

The overall uncertainty budget for both BS EN 1021: Part 1 and 2:2014 is as follows:-

Timings: ±2 seconds.

Reported by: Countersigned By: P Doherty

Laboratory Technician Manager

Enquiries concerning this report should be addressed to Customer Services.

