

TOPIC & TOPIC SOFT

Design/Colorscale	Pepe Comi/Dorte Bo Bojesen
Material	100% Polyester, Trevira CS
Care instructions	Remove dust with a damp cloth or a brush
Width.....	300 cm (± 1%) 118" (± 1%)
Weight.....	118 g/m ² (± 5%) 3,5 oz/yd ² (± 5%)
Thickness	0,34 mm 13,4 mil
Standard Roll Length (approx)	50 m 55 yd
Breaking strength ISO 13934-1	Warp: 127-145 N Weft: 155-176 N
Elongation to break ISO 13934-1	Warp: 54-65% Weft: 22-27%
Fastness to light ISO 105B02 (Bluescale 1-8)	Class 5-7
Openess factor	29%

Flame retardant according to:

DIN 4102 (B1)	(Topic & Topic Soft)
BS 5967: Part 2: Type B	(Topic & Topic Soft)
EN 13773 Class 1	(Topic)
IMO FTP Code 2010: Part 7	(Topic)
NFP 92-503-507 (M1)	(Topic)
UNI 9177 Classe 1	(Topic)




0575





The Topic product is available in 2 versions. Topic Soft is suitable for curtain installation and Topic is suitable for roller blind and panel installations. Each individual article in this hanger is labeled accordingly, see tab on the back of each colorway indicating if the version shown is Topic Soft or Topic. For more colorway options of Topic Soft please see our website or contact your sales representative.

USAGE TOPIC

Panels:



Rollerblinds:



Normal rolling

Reversed rolling

Maximum drop

Vertical stripes
Horizontal stripes

	Yes	Yes	Yes	9 m ²
	Not recommended	Yes ¹	Yes ¹	3 m

All articles intended for indoor usage behind glass. It is strongly recommended to use ultra sonic, laser or cutter with knife for cutting and shaping the screens. Handle with care during sewing and installation, be sure to avoid wrinkles and crease. Fabric shade may vary slightly between batches.

1= Fabric rolls are rolled reverse side out. Roller blind tube should be placed on the reverse side of the fabric to prevent curling.

2= Svensson guarantee flawless cut measurements up to 9 m. Installations with cut measurements larger than 9 m are possible, but the customer is responsible for material cost due to increased fabric wastage.

TOPIC	Solar optical properties (%) according to EN 14500					Thermal performance in combination with reference glazings from EN 14501							
	Ts	Rs	As	T _{vis}	T _{uv}	Glazing A		Glazing B		Glazing C		Glazing D	
Colour						g _{tot}	U	g _{tot}	U	g _{tot}	U	g _{tot}	U
8000	59	39	2	59	42	0,58	5,54	0,56	2,68	0,48	1,17	0,28	1,14
4030	58	29	13	52	43	0,64	5,51	0,60	2,67	0,51	1,17	0,29	1,14
8400	51	21	28	42	37	0,68	5,29	0,64	2,61	0,53	1,15	0,30	1,13
8500	47	21	32	32	33	0,68	5,18	0,64	2,57	0,53	1,14	0,30	1,12
6710	61	35	4	61	45	0,61	5,60	0,58	2,70	0,49	1,18	0,28	1,15
8100	58	33	9	55	43	0,61	4,90	0,58	2,49	0,50	1,12	0,28	1,09
3220	54	30	16	48	39	0,62	4,86	0,59	2,48	0,50	1,12	0,29	1,09
7080	46	21	33	32	33	0,67	5,16	0,63	2,57	0,53	1,14	0,30	1,12
6402	54	33	13	52	38	0,59	4,84	0,57	2,47	0,49	1,11	0,28	1,09
6927	51	25	24	40	33	0,66	5,29	0,62	2,61	0,52	1,15	0,30	1,13
3427	49	24	27	35	32	0,66	5,24	0,62	2,59	0,52	1,15	0,30	1,12
3744	52	23	26	38	37	0,66	4,90	0,62	2,49	0,52	1,12	0,30	1,09
4362	47	18	27	33	34	0,68	4,83	0,64	2,47	0,53	1,11	0,30	1,09
4421	57	31	13	51	42	0,62	4,85	0,59	2,47	0,50	1,12	0,29	1,09
4270	52	19	29	37	37	0,70	5,32	0,65	2,61	0,54	1,15	0,31	1,13
3611	57	34	9	53	42	0,60	4,86	0,57	2,48	0,49	1,12	0,28	1,09
4653	51	22	27	40	39	0,66	4,91	0,62	2,49	0,52	1,12	0,30	1,09
5051	50	22	29	38	36	0,66	4,87	0,62	2,48	0,52	1,11	0,30	1,09
6335	55	26	19	48	37	0,65	5,54	0,62	2,68	0,52	1,17	0,30	1,14
7030	54	31	15	48	38	0,63	5,38	0,60	2,63	0,50	1,16	0,30	1,13

T_{uv} = Solar Transmission T_{uv} = Ultraviolet Transmission
 Rs = Solar Reflection g_{tot} = Total solar energy transm. (0-1) 1=100%
 As = Solar Absorption U = Thermal transmittance W/m² K
 T_{vis} = Visible light Transm.

Glazing A = Clear single glazing, g=0,863, U=5,88
 Glazing B = Clear double glazing, g=0,762, U=2,88
 Glazing C = Double glazing with low e coating, g=0,59, U=1,23
 Glazing D = Refl. double glazing with low e coating, g=0,334, U=1,2