

Telephone: +44 (0)113 259 1999

Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 27 February 2020

Our Ref: 23/57320-1-1 Your Ref: -

Page: 1 of 6

PClient: AB Ludvig Svensson

511 82 Kinna Sweden

Job Title: BS EN 1021 Parts 1 & 2

Client's Order No:

Date of Receipt: 17 February 2020 Date of Test Start: 25 February 2020

Description of Sample(s): One sample of fabric identified as follows was received for testing:

Debut, stated to be 78% wool, 12% Ramie, 10% viscose

Work Requested: We were asked to make the following test:

BS EN 1021-1:2014 and BS EN 1021-2 2014





Telephone: +44 (0)113 259 1999

Email: <u>info@bttg.co.uk</u> Website: <u>www.bttg.co.uk</u>

Date: 27 February 2020

Our Ref: 23/57320-1-1 Your Ref: -

Page: 2 of 6

AB Ludvig Svensson

Sample was identified as follows:

Debut, stated to be 78% wool, 12% Ramie, 10% viscose

FIRE TESTS ACCORDING TO BS EN 1021-1:2014

Assessment of the ignitability of upholstered furniture. Part I. Ignition Source 0: Smouldering cigarette

Pre-Treatment

The sample was water-soaked and dried in accordance with BS EN 1021 Part 1:Annex D.

Conditioning

The sample was conditioned for at least 16 hours at a temperature of 23±2°C and relative humidity of 50±5%.

The sample was tested in a room of volume 25m³ and 16°C.

Procedure

The test was carried out in accordance with BS EN 1021-1:2014. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The sample was tested over non-fire retardant polyurethane foam with a density of approximately 20-22 kg/m³.

Tests were made using ignition source 0.

Requirements

The specimens shall not:-

Smouldering Criteria

- a) display escalating combustion requiring active extinction.
- b) smoulder or burn until it is essentially consumed within the test duration.
- c) smoulder or burn to the extremities of the specimen, or through the full thickness, within the duration of the test.
- d) smoulder for more than one hour.
- e) on final examination, show evidence of progressive smouldering.





Telephone: +44 (0)113 259 1999

Email: info@bttg.co.uk Website: www.bttg.co.uk

Date: 27 February 2020

Our Ref: 23/57320-1-1 Your Ref: -

Page: 3 of 6

AB Ludvig Svensson

Requirements (continued)

Flaming Criteria

a) show evidence of flaming initiated by a smouldering source.

Results

	Cigarette			_
	1	2	3 ¹	Comments
Smouldering Criteria (Yes/No)				
Unsafe escalating combustion	No	No	No	
Test assembly consumed	No	No	No	
Smoulders to extremities	No	No	No	
Smoulders through thickness	No	No	No	
Smoulders more than1 hour	No	No	No	
In final examination, presence of progressive smouldering	No	No	No	
Ignitability Performance (Yes/No)				
Occurrence of flames	No	No	No	
Ignition / Non Ignition (I/NI)	NI	NI	NI	

¹ Results for cigarette 3, only if applicable.

Note

The test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Comments

An NI designation indicates that the sample meets the performance requirements of BS EN 1021-1.





Telephone: +44 (0)113 259 1999

Email: <u>info@bttg.co.uk</u> Website: <u>www.bttg.co.uk</u>

Date: 27 February 2020

Our Ref: 23/57320-1-1 Your Ref: -

Page: 4 of 6

AB Ludvig Svensson

FIRE TESTS ACCORDING TO BS EN 1021-2:2014

Assessment of the ignitability of upholstered furniture. Part 2. Ignition Source 1: Match flame equivalent.

Pre-Treatment

The sample was water-soaked and dried in accordance with BS EN 1021 Part 1:Annex D.

Conditioning

The sample was conditioned for at least 16 hours at a temperature of 23±2°C and relative humidity of 50±5%.

The sample was tested in a room of volume 25m³ and 16°C.

Procedure

The test was carried out in accordance with BS EN 1021-2:2014. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The sample was tested over non-fire retardant polyurethane foam with a density of approximately 20-22 kg/m³.

Tests were made using ignition source 1.

Requirements

The specimens shall not:-

Smouldering Criteria

- a) display escalating combustion requiring active extinction.
- b) smoulders until it is essentially consumed within the test duration.
- c) smoulder to the extremities of the specimen, or through the full thickness, within the duration of the test.
- d) smoulder for more than one hour.
- e) show evidence of charring, other than discolouration, for more than 100mm in any direction apart from the nearest part of the original position of the source.





Telephone: +44 (0)113 259 1999 Email: <u>info@bttg.co.uk</u>

Website: www.bttg.co.uk

Date: 27 February 2020

Our Ref: 23/57320-1-1 Your Ref: -

Page: 5 of 6

AB Ludvig Svensson

Requirements (Continued)

Flaming Criteria

- a) display escalating combustion requiring active extinction.
- b) burns until it is essentially consumed within the test duration.
- c) burns to the extremities of the specimen, or through the full thickness, within the duration of the test.
- d) exhibit any flaming for more than 120 seconds after removal of the burner tube.

Results

		h Flame	
	Equivalent		Comments
	1	2	
Smouldering Criteria (Yes/No)			
Unsafe escalating combustion	No	No	
Test assembly consumed	No	No	
Smoulders to extremities	No	No	
Smoulders through thickness	No	No	
Smoulders more than 1 hour	No	No	
In final examination, presence of	No	No	
progressive smouldering	NO	INO	
Ignitability Performance (Yes/No)			
Unsafe escalating combustion	No	No	
Test assembly consumed	No	No	
Flames to extremities	No	No	
Flames through thickness	No	No	
Flames longer than 120 seconds	No	No	
Ignition / Non Ignition (I/NI)	NI	NI	

Note

The test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.





Telephone: +44 (0)113 259 1999

Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 27 February 2020

Our Ref: 23/57320-1-1 Your Ref: -

Page: 6 of 6

AB Ludvig Svensson

Comments

An NI designation indicates that the sample meets the performance requirements of BS EN 1021-2.

This report relates only to the samples submitted and as described in the report.

The overall uncertainty budget for both BS EN 1021: Part 1 and 2:2014 is as follows:-

Timings: ±2 seconds.

Reported by: Countersigned By:

B Bland P Doherty Laboratory Technician Manager

Enquiries concerning this report should be addressed to Customer Services.

