



TEST REPORT

Client: AB Ludvig Svensson
 Bangatan 8
 SE-511 82 Kinna
 Sweden

Entry No: 72626

Date received: 16/11/2015

Client's Description: Sample of fabric article: Ombre, Composition: 100% Trevira CS, Weight: 220 g/m²

Test Required: Flammability BS 5867-2 : Type B

Pre-treatment: none

Conditioning: A minimum of 24 hours at 65+/-5% Relative Humidity, 20+/-2°C

Date Tests Completed: 18/11/2015

Method of Test: BS EN ISO 15025 : 2002 Procedure A (surface ignition)

The results may not apply to situations where there is restricted air supply or prolonged exposure to large sources of intense heat as in a conflagration.

Flame application time 15 seconds using propane gas

Face of Fabric tested	Fabric length direction			Fabric width direction		
	1↑	2↓	3↑	4→	5←	6→
Specimen number						
Flame reached an edge (✓ or X)	X	X	X	X	X	X
Hole reached an edge (✓ or X)	X	X	X	X	X	X
Flaming debris (✓ or X)	X	X	X	X	X	X

Comments

On the basis of the tests carried out this sample of fabric meets the Type B requirements of BS 5867-2: 2008.

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein



Dale Brockbank
 Materials Testing Manager
 18 November 2015

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
 - ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
 - ❖ Uncertainty budgets for test methods contained within this report are available on request.
- This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



1104