

# **Confidential Report**

Our Ref: 23/62084A/05/24







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 28 May 2024

Our Ref: 23/62084A/05/24

Your Ref: ---

Page: 1 of 5

Client: AB Ludvig Svensson

Bangatan 8 511 82 Kinna Sweden

Job Title: Fire Test on One Fabric Sample

Clients Order Ref: --

Date of Receipt: 17 May 2024

Date Test Started: 23 May 2024

Description of Sample: One sample of fabric, which was referenced by the client as;

Seam, 100% Trevira

Work Requested: We were asked to make the following fire test:

IMO FTP Code 2010:Part 7

- subcontracted test, UKAS accredited
- \*\* subcontracted test, EN ISO/IEC 17025 accredited
- \*\*\* not UKAS accredited



Note: This report relates only to the items tested.



Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 28 May 2024

Our Ref: 23/62084A/05/24

Your Ref:

Page: 2 of 5

**Client: AB Ludvig Svensson** 

## **Product Description**

Company Name	AB Ludvig Svensson			
Type of Material, i.e. Curtain, Drape, etc.	Curtain fabric			
Name and/or Identification of the Product Tested	Seam			
Mass per Unit Area (g/m²)	280			
Thickness (mm)	-			
Colour and Tone (i)	Green			
Quantity and Number of Any Coating	None			
Method and Quantity of Fire-Retardant Treatment	Permanently flame retardant fibre			
Materials of the Product and its Composite Ratio (ii)	100% Trevira CS			
Composition of Weave (iii)	weave			
Density (Number/Inch) the Number of Threads per Inch in both warp and weft; and	Warp: 93 Weft: 64			
Yarn Number Count	Nm 60/2; Nm 15/2			

- (i) If the product has a pattern, the representative colour shall be described.
- (ii) Such as wool, nylon, polyester, etc.
- (iii) Such as plain, weave, twilled.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 28 May 2024

Our Ref: 23/62084A/05/24 Your Ref:

Page: 3 of 5

Client: **AB Ludvig Svensson** 

# FIRE TESTS ACCORDING to IMO FTP Code 2010:Part 7 Test for Vertically Supported Textiles and Films

## **Cleaning Procedure**

The sample received no pre-treatment as the fabric was stated to be inherently flame retardant.

## **Conditioning**

The sample was conditioned for not less than 24 hours in the standard atmosphere for conditioning textiles of 20±5°C and 65  $\pm$  5% R.H.

#### **Procedure**

The sample was tested in accordance with IMO FTP Code 2010:Part 7\*. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

A 40mm high propane gas flame was applied to the edge of 5 warp and 5 weft specimens for 15 seconds.

The after-flame time, length of char, existence of surface flashing and ignition of cotton waste from drops were recorded.

#### \*Deviation from standard

The test was carried out in a test enclosure to different dimensions to that specified in IMO FTP Code 2010:Part 7. The dimensions of the test enclosure are 1820mm wide x 1220mm deep x 1950mm. The test was carried out in a draught free enclosure.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 28 May 2024

Our Ref: 23/62084A/05/24 Your Ref:

> Page: 4 of 5

Client: **AB Ludvig Svensson** 

## Requirements

The Performance Criteria for Curtains and Drapes states that: Products which show any of the following characteristics obtained by the fire test in appendix 1, shall be considered unsuitable for use as curtains, drapes or free-hanging fabric product for use in rooms containing furniture and furnishings of restricted fire risk as defined in the relevant regulations of chapter II-2 of the Convention:-.

- An after-flame time greater than 5 sec for any of the 10 or more specimens tested with surface application of the pilot flame.
- 2. Burn through to any edge of any of the 10 or more specimens tested with surface application of the pilot flame.
- Ignition of cotton wool below specimen in any of the 10 or more specimens tested.
- An average char length in excess of 150mm observed in any of the 10 or more specimens tested by either surface or
- 5. The occurrence of a surface flash propagating more than 100mm from the point of ignition with or without charring of the base fabric.

If it is found that either or both of the batches of five specimens cut in both warp and weft directions fail to meet one or more of the criteria specified in subparagraphs .1 to .3 and .5 above because of poor performance of only one of the five specimens tested, one complete retest of a similar batch is permitted. Failure of the second batch to meet any of the criteria shall provide the basis for rejection of the fabric for use.

### Results

	After flame time (s)		Char length (mm)		Flaming to edge (yes or No)		Ignition of Cotton Wool from Flaming Drops (Yes or No)		Surface Flashing (Yes or No), if yes, Propagation Length (mm)	
	Warp	Weft	Warp	Warp	Weft	Weft	Warp	Weft	Warp	Weft
	0	0	84	70	No	No	No	No	No	No
	0	0	81	73	No	No	No	No	No	No
	0	0	69	82	No	No	No	No	No	No
	0	0	77	76	No	No	No	No	No	No
	0	0	78	80	No	No	No	No	No	No
Mean	0	0	78	76						







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 28 May 2024

Our Ref: 23/62084A/05/24

Your Ref:

Page: 5 of 5

Client: **AB Ludvig Svensson** 

#### Note

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

#### Comment

The results indicate the sample meets the requirements according to IMO 2010 FTP Code, Part 7.

Where required to make a judgement to any pass/fail criteria an estimation of uncertainty of measurement has been taken into account. Under our Policy we have used a non-binary decision rule.

See our decision rules Policy (<a href="https://www.bttg.co.uk/about-us/decision-rules-policy/">https://www.bttg.co.uk/about-us/decision-rules-policy/</a>) for further information.

## **Uncertainty Budget**

The overall uncertainty budget IMO FTP Code 2010:Part 7 is as follows:-

Measurements: ±2mm **Duration of Flaming:** ±2 seconds

Reported by:..... .....R Greasley, Laboratory Technician

.... B Bland, Technical Customer Service Officer Countersigned by:....

Enquiries concerning this report should be addressed to Customer Services.



