

## **Confidential Report**

Our Ref: 23/58931A/09/21





Telephone: +44 (0) 113 259 1999

Email: <u>info@bttg.co.uk</u> : <u>www.bttg.co.uk</u>

Date: 29 September 2021

Our Ref: 23/58931A/09/21

Your Ref: ---

Page: 1 of 6

Client: Svensson

AB Ludvig Svensson Bangatan 8 SE - 511 82 Kinna Sweden

Job Title: Fire Test on One Fabric Sample

Clients Order Ref: ---

Date of Receipt: 20 September 2021

Date Test Started: 27 September 2021

Description of Sample: One sample of fabric, which was referenced by the client as;

Article: Airy

Composition: 100% Trevira CS

Weight: 115g/m<sup>2</sup>

Work Requested: We were asked to make the following fire test:

IMO FTP Code 2010:Part 7

- subcontracted test, UKAS accredited
- \*\* subcontracted test, EN ISO/IEC 17025 accredited
- \*\*\* not UKAS accredited

Note: This report relates only to the samples submitted and as described in the report.

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.

A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.

BTTG<sup>TM</sup> and Shirley® are trade names of Shirley Technologies Ltd.

The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.

Our laboratories are accredited to EN ISO/IEC 17025.





Telephone: +44 (0) 113 259 1999 Email: <u>info@bttg.co.uk</u>

: www.bttg.co.uk

Date: 29 September 2021

Our Ref: 23/58931A/09/21

Your Ref: ---

Page: 2 of 6

Client: Svensson

## **Product Description**

Company Name	AB Ludvig Svensson			
Type of Material, i.e. Curtain, Drape, etc.	Curtain Fabric			
Name and/or Identification of the Product Tested	Airy			
Mass per Unit Area (g/m²)	115			
Thickness (mm)				
Colour and Tone (i)	Blue			
Quantity and Number of Any Coating	None			
Method and Quantity of Fire-Retardant Treatment	Permanently flame retardant fibre			
Materials of the Product and its Composite Ratio (ii)	100% Trevira CS			
Composition of Weave (iii)	Weave			
Density (Number/Inch) the Number of Threads per Inch in both warp and weft; and	Warp: 27, Weft: 14			
Yarn Number Count	Nm 40/2; Nm 15/2			

- (i) If the product has a pattern, the representative colour shall be described.
- (ii) Such as wool, nylon, polyester, etc.
- (iii) Such as plain, weave, twilled.





Telephone: +44 (0) 113 259 1999

Email: <u>info@bttg.co.uk</u> : <u>www.bttg.co.uk</u>

Date: 29 September 2021

Our Ref: 23/58931A/09/21

Your Ref: ---

Page: 3 of 6

Client: Svensson

# FIRE TESTS ACCORDING to IMO FTP Code 2010:Part 7 Test for Vertically Supported Textiles and Films

## **Cleaning Procedure**

The sample received was tested as received.

## **Conditioning**

The sample was conditioned for not less than 24 hours in the standard atmosphere for conditioning textiles of  $20\pm$  5°C and  $65\pm5\%$  R.H.

#### **Procedure**

The sample was tested in accordance with IMO FTP Code 2010:Part 7\*. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

A 40mm high propane gas flame was applied to the edge of 5 warp and 5 weft specimens for 15 seconds.

The after-flame time, length of char, existence of surface flashing and ignition of cotton waste from drops were recorded.

#### \*Deviation from standard

The test was carried out in a test enclosure to different dimensions to that specified in IMO FTP Code 2010:Part 7. The dimensions of the test enclosure are 1820mm wide x 1220mm deep x 1950mm. The test was carried out in a draught free enclosure.





Telephone: +44 (0) 113 259 1999

Email: <u>info@bttg.co.uk</u> : www.bttg.co.uk

Date: 29 September 2021

Our Ref: 23/58931A/09/21

Your Ref: ---

Page: 4 of 6

Client: Svensson

## Requirements

The Performance Criteria for Curtains and Drapes states that: Products which show any of the following characteristics obtained by the fire test in appendix 1, shall be considered unsuitable for use as curtains, drapes or free-hanging fabric product for use in rooms containing furniture and furnishings of restricted fire risk as defined in the relevant regulations of chapter II-2 of the Convention:-.

- 1. An after-flame time greater than 5 sec for any of the 10 or more specimens tested with surface application of the pilot flame.
- 2. Burn through to any edge of any of the 10 or more specimens tested with surface application of the pilot flame.
- 3. Ignition of cotton wool below specimen in any of the 10 or more specimens tested.
- 4. An average char length in excess of 150mm observed in any of the 10 or more specimens tested by either surface or edge ignition; and
- 5. The occurrence of a surface flash propagating more than 100mm from the point of ignition with or without charring of the base fabric.

If it is found that either or both of the batches of five specimens cut in both warp and weft directions fail to meet one or more of the criteria specified in subparagraphs .1 to .3 and .5 above because of poor performance of only one of the five specimens tested, one complete retest of a similar batch is permitted. Failure of the second batch to meet any of the criteria shall provide the basis for rejection of the fabric for use.





Telephone: +44 (0) 113 259 1999

Email: info@bttg.co.uk : www.bttg.co.uk

Date: 29 September 2021

Our Ref: 23/58931A/09/21 Your Ref: ---

Page: 5 of 6

Client: Svensson

### **Test Results**

### As Received

	After flame time (s)				Flaming to edge (yes or No)		Ignition of Cotton Wool from Flaming Drops (Yes or No)		Surface Flashing (Yes or No), if yes, Propagation Length (mm)	
	Warp	Weft	Warp	Warp	Weft	Weft	Warp	Weft	Warp	Weft
	0	0	154	114	No	No	No	No	No	No
	0	0	113	129	No	No	No	No	No	No
	0	0	132	146	No	No	No	No	No	No
	0	0	117	121	No	No	No	No	No	No
	0	0	133	140	No	No	No	No	No	No
Mean	0	0	130	130						

## **Comment**

The results indicate the sample meets the requirements according to IMO 2010 FTP Code, Part 7.





Telephone: +44 (0) 113 259 1999

Email: info@bttg.co.uk : www.bttg.co.uk

Date: 29 September 2021

Our Ref: 23/58931A/09/21 Your Ref: ---

rodi iteli

Page: 6 of 6

Client: Svensson

An estimation of uncertainty of measurement has been taken into account when making a judgment to any pass/fail criteria. Under our Policy we have used a non-binary decision rule.

See our Decision rules Policy (<a href="http://www.bttg.co.uk/decision-rules-policy">http://www.bttg.co.uk/decision-rules-policy</a>) for further information.

## **Uncertainty Budget**

The overall uncertainty budget IMO FTP Code 2010:Part 7 is as follows:-

Measurements: ±1mm

Duration of Flaming: ±0.5 seconds

Reported by: B Bland, Technical Customer Service Officer

Countersigned by:...... P Doherty, Manager

Enquiries concerning this report should be addressed to Customer Services.

