



Confidential Report

Our Ref: 23/58193-1-1



1066

Notified Body
for PPE Directive,
Construction Products Regulation
& Marine Equipment Directive
I.D. No. 0338 & 0339



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 8 February 2021

Our Ref: 23/58193-1-1
Your Ref: -

Page: 1 of 5

Client: AB Ludvig Svensson
511 82 Kinna
Sweden

Job Title: Fire Test on One Sample of Fabric

Client's Order No: -

Date of Receipt: 1 February 2021

Description of Sample(s): One sample of fabric identified as follows was received for testing:
Noun, stated to be 100% Trevira CS

Work Requested: We were asked to make the following test(s):
IMO FTP Code 2010 Part 7

- * subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
BTTG™ and Shirley® are trade names of Shirley Technologies Limited
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.
Copyright © 2021 Shirley Technologies Limited. All rights reserved.



TESTING • CERTIFICATION • AUDITING

Client: AB Ludvig Svensson

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.

Telephone: +44 (0) 113 259 1999

Email: info@bttg.co.uk

Website: www.bttg.co.uk

Date: 8 February 2021

Our Ref: 23/58193-1-1

Your Ref: -

Page: 2 of 5

Product Description

Company Name	AB Ludvig Svensson
Type of Material, i.e. Curtain, Drape, etc.	Curtain
Name and/or Identification of the Product Tested	Noun
Mass per Unit Area (g/m ²)	260 g/m ² approx.
Thickness (mm)	Not supplied by client
Colour and Tone (i)	Turquoise & Black
Quantity and Number of Any Coating	None
Method and Quantity of Fire-Retardant Treatment	Permanently flame retardant fibre
Materials of the Product and its Composite Ratio (ii)	100% Trevira CS
Composition of Weave (iii)	Plain
Density (Number/Inch) the Number of Threads per Inch in both warp and weft; and	Warp:131, Weft: 99
Yarn Number Count	Nm 60/2, dtex 167

- (i) If the product has a pattern, the representative colour shall be described.
- (ii) Such as wool, nylon, polyester, etc.
- (iii) Such as plain, weave, twilled.



1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.

A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.

BTTG™ and Shirley® are trade names of Shirley Technologies Limited

The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.

Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2021 Shirley Technologies Limited. All rights reserved.



TESTING • CERTIFICATION • AUDITING

Client: AB Ludvig Svensson

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@btg.co.uk
Website: www.btg.co.uk

Date: 8 February 2021

Our Ref: 23/58193-1-1
Your Ref: -

Page: 3 of 5

FIRE TESTS ACCORDING to IMO FTP Code 2010:Part 7 Test for Vertically Supported Textiles and Films

Cleaning Procedure

The sample received no pre-treatment as the fabric was stated to be inherently flame retardant.

Conditioning

The sample was conditioned for not less than 24 hours in the standard atmosphere for conditioning textiles of $20 \pm 5^\circ\text{C}$ and $65 \pm 5\%$ R.H.

Procedure

The sample was tested in accordance with IMO FTP Code 2010:Part 7*. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

A 40mm high propane gas flame was applied to the edge of 5 warp and 5 weft specimens for 15 seconds.

The after-flame time, length of char, existence of surface flashing and ignition of cotton waste from drops were recorded.

*Deviation from standard

The test was carried out in a test enclosure to different dimensions to that specified in IMO FTP Code 2010:Part 7. The dimensions of the test enclosure are 1820mm wide x 1220mm deep x 1950mm. The test was carried out in a draught free enclosure.

Requirements

The Performance Criteria for Curtains and Drapes states that: Products which show any of the following characteristics obtained by the fire test in appendix 1, shall be considered unsuitable for use as curtains, drapes or free-hanging fabric product for use in rooms containing furniture and furnishings of restricted fire risk as defined in the relevant regulations of chapter II-2 of the Convention:-.

1. An after-flame time greater than 5 sec for any of the 10 or more specimens tested with surface application of the pilot flame.
2. Burn through to any edge of any of the 10 or more specimens tested with surface application of the pilot flame.
3. Ignition of cotton wool below specimen in any of the 10 or more specimens tested.
4. An average char length in excess of 150mm observed in any of the 10 or more specimens tested by either surface or edge ignition; and
5. The occurrence of a surface flash propagating more than 100mm from the point of ignition with or without charring of the base fabric.





TESTING • CERTIFICATION • AUDITING

Client: AB Ludvig Svensson

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
 Telephone: +44 (0) 113 259 1999
 Email: info@bttg.co.uk
 Website: www.bttg.co.uk

Date: 8 February 2021

Our Ref: 23/58193-1-1
 Your Ref: -

Page: 4 of 5

If it is found that either or both of the batches of five specimens cut in both warp and weft directions fail to meet one or more of the criteria specified in subparagraphs .1 to .3 and .5 above because of poor performance of only one of the five specimens tested, one complete retest of a similar batch is permitted. Failure of the second batch to meet any of the criteria shall provide the basis for rejection of the fabric for use.

As Received

	After flame time (s)		Char length (mm)		Flaming to edge (yes or No)		Ignition of Cotton Wool from Flaming Drops (Yes or No)		Surface Flashing (Yes or No), if yes, Propagation Length (mm)	
	Warp	Weft	Warp	Weft	Warp	Weft	Warp	Weft	Warp	Weft
	0	0	47	38	No	No	No	No	No	No
	0	0	40	45	No	No	No	No	No	No
	0	0	39	42	No	No	No	No	No	No
	0	0	37	37	No	No	No	No	No	No
	0	0	44	55	No	No	No	No	No	No
Mean	0	0	41	44						


Comment

The results indicate the sample meets the requirements according to IMO 2010 FTP Code, Part 7.

This report relates only to the samples submitted and as described in the report.

Uncertainty of measurement has not been taken into account when presenting the test result. The relevant uncertainty value is included as an annex which forms an integral part of the report.

Reported by: 
 B Bland
 Laboratory Technician

Countersigned By: 
 P Doherty
 Manager





TESTING • CERTIFICATION • AUDITING

Client: AB Ludvig Svensson

Wira House, West Park Ring Road, Leeds, LS16 6QL, UK.
Telephone: +44 (0) 113 259 1999
Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 8 February 2021

Our Ref: 23/58193-1-1
Your Ref: -

Page: 5 of 5

Uncertainty Budget - Annex

The overall uncertainty budget IMO FTP Code 2010:Part 7 is as follows:-

Measurements: $\pm 1\text{mm}$
Duration of Flaming: ± 0.5 seconds

