



# West Yorkshire Materials Testing Service

PO Box 5, Morley, LS27 0QP  
Nepshaw Lane South, Morley, Leeds  
Tel 0113 253 0241 Fax 0113 252 7029  
**Head of Laboratory G. Briggs C. Text ATI**

Page 1 of 1

**Client:** AB Ludvig Svensson  
Bangatan 8  
SE-511 82 Kinna  
Sweden

**Entry No:** 48695 (Amended)

**Date received:** 09/11/2011

**Client's Description:** Sample of fabric Juno composition 100% Trevira CS

## TEST REPORT

**Test Required:** Flammability in accordance with BS 5852 ignition source 5  
**Pre-treatment:** None  
**Conditioning:** A minimum of 96 hours at 50 +/- 5% Relative Humidity, 23 +/- 2°C  
**Method of Test:** BS 5852 : 2006 Clause 11 (composites)  
**Date of Test:** 17/11/2011

The following test results relate only to the ignitability of the combination of upholstery composites under the particular conditions of test. They are not intended as a means of assessing the full potential fire hazard of the materials in use.

Ignition Source	Observations	Result
5 (Wood Crib)	Flaming ceased within the specified ten minute period after ignition of the crib and no progressive smouldering occurred.	PASS

**Note:** A 35 kg/m<sup>3</sup> CMHR Foam (Carpenters RX36-125) was used as the filling.

-----End of Document-----

*This is hereby certified to be a correct return of the tests made of the items referred to herein.*



G Briggs, Head of Laboratory  
Date of original 7<sup>th</sup> December 2011  
Date of amendment 8<sup>th</sup> December 2011

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
- ❖ Test marked (\*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
- ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
- ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

